

Product Specifications: Suede

Abrasion	ASTM D 4157 150,000 double rubs with cotton duck
Tensile	ASTM D 5034 188.3 lbs. Warp 232.1 lbs. Fill
Tear	ASTM 2261 6.1 lbs. Warp 17.5 lbs. Fill
Seam Slippage	ASTM D 4034: 125lbs. Warp 106.5 lbs. Fill
Pilling	UPH #106: Class 4.5
Color Fastness	AATCC 8 Wet Procedure Class 3 min
Moisture Resistance	Suter AATCC 127 100 average cm.
Flame Retardency	Pass UFAC Class 1 NFPA 260 California 117
Microbial Resistance	Bacterica Testing Fungal Testing Excellent Properties
Fiber Content	100% polyester
Stain Resistance	Class 4-5 AATCC 130 Soil Release-Oily Stain Release